

UNCLASSIFIED

Defense Technical Information Center  
Compilation Part Notice

ADP012734

TITLE: One-Dimensional Miniband Transport in Doped GaAs/AlAs Superlattices

DISTRIBUTION: Approved for public release, distribution unlimited  
Availability: Hard copy only.

This paper is part of the following report:

TITLE: Nanostructures: Physics and Technology International Symposium [6th] held in St. Petersburg, Russia on June 22-26, 1998 Proceedings

To order the complete compilation report, use: ADA406591

The component part is provided here to allow users access to individually authored sections of proceedings, annals, symposia, etc. However, the component should be considered within the context of the overall compilation report and not as a stand-alone technical report.

The following component part numbers comprise the compilation report:

ADP012712 thru ADP012852

UNCLASSIFIED

## One-dimensional miniband transport in doped GaAs/AlAs superlattices

*Yu. A. Pusep, A. J. Chiquito, S. Mergulhão and J. C. Galzerani*

Departamento de Física, Universidade Federal de São Carlos, 13565-905 São Carlos, SP, Brasil

Evidence of the crucial role of random fluctuations of the well size in vertical transport in doped GaAs/AlAs superlattices with broad minibands has been obtained by both Fourier-transform reflection spectroscopy and C–V measurements. The samples with different density of free electrons and, as a consequence, with different filling of the miniband were examined.

It turned out that even monolayer fluctuations of the periodicity, or random fluctuations of the impurity potentials, which are unavoidable, can cause a partial localization of electrons providing one-dimensional conducting channels where the periodicity is conserved, and through which the electron transport across the superlattice would occur.

This was found to be the reason why, instead of the constant vertical conductivity (independent of the electron density) predicted by the theory to occur when the Fermi energy exceeds the miniband width, a drop of the conductivity giving a metal-to-dielectric phase transition was observed.

The percentage of the electron states localized in the lowest miniband was determined in the superlattices with different electron concentrations and with different miniband widths. This showed the increase of a number of the localized states with increase of the electron concentration and with decrease of the miniband width.